Philadelphia Apl 18 1892

The Specimen of gold colored silver was obtained by reduction of silver tartrate with ferrous tartrate. The white silver sent was originally gold colored and after a time perhaps a year, the Specimen of gold colored will also turn white. spontaneously and in the dark. Continuous shaking like that of a rail road train will sometimes start the change. For this reason I have stuffed the vial with cotton to diminish the friction of the pieces against each other.

The brilliant surface of the gold colored silver is natural and the pieces are sent just as they

M Carey Lea